

# Data sheet

## mediaJET® PGC 260FD Premium

Premium photo paper, fast dry

### Product description:

High gloss photo paper for presentation prints, posters, photo reproductions, a.s.o... Can be printed extremely well with pigmented and dye ink, wipe-resistant drying immediately after printing, universal utilisation, very good ink saturation.

### Specific feature:

Universally applicable weighty photo-glossy paper with a high-glossy surface which shows a practically immediate smearless drying and excellent water resistance. Color images are reproduced in an almost photorealistic way, true colors, living and rich in detail. MediaJet® PGC 260FD is a high-quality photo paper for the universal use on all common LFP inkjet plotters using dye-based as well as pigmented inks. The coating of this genuine photo basic paper shows an excellent color reproduction at high truth of detail, sharpness of outline, an extreme great color complexity and excellent flatness. MediaJet® PGC 260FD is an inkjet paper for highest requirements. The glossy PGC 260 Premium with high resolution can be laminated cold. Due to its robust surface in many cases lamination is not necessary when used in the indoor area.

### Processing:

For optimum printing results, MediaJet® PGC 260FD must be calibrated beforehand on the used printers and with the appropriate ink. Without calibration color modifications can occur. For quality reasons the processing and storage of MediaJet® PGC 260FD should take place in a climate of about 50% relative humidity and at a temperature of about 23°C. Keep in the original packing carton box and PE-bag at a cool and dry place, clean and dustfree.

### Technical specification:

Material:	PAPIER
Application Area:	NUR IM INNENBEREICH
Surface:	GLAENZEND
Specific gravity:	260,00g/m <sup>2</sup>
Thickness:	265,00µm
B1-cert.:	nein
Cold lamination:	ja
water resistant:	ja
Opacity:	96% ±3 ISO 2471
Color L:	95,48 ±0,5
Color a:	-0,19 ±0,3
Color b:	-4,4 ±0,5
Whiteness (R457):	92% ±3 ISO 2470
Specular gloss:	58% ±5 bei 75° ISO 8254-1
Glätte: >10.000s ISO 5627:	
Steifigkeit md:	1,9mN ±0,8 ISO 2493
Steifigkeit cd:	1,4mN ±0,5 ISO 2493
DIN ISO 16245	Nein

This information consists of standard values for your guidance. Before using our print media, please check their suitability to your printer and for your intended application. Taking account of technical development, product specifications may be amended without prior notice at any time. There is no guarantee that the same results can be achieved. We can not accept liability for any errors resulting from technical changes in printers and / or inks.