

**mediaJET® PEARL 300 „bright white“ | Portrait photo paper FastDry**

---

**Product description**

A professional portrait photo paper with beautiful whiteness and classic pearl gloss effect. An absolutely perfect all-rounder for outstanding image quality without reflections. The velvety lustre surface refines the image output on a modern photo paper that is almost insensitive to mechanical abrasion and fingerprints.

**Specific feature**

Universally applicable weighty photo satin paper with a „pearl“ finish which shows a practically immediate smearless drying. Colour images are reproduced in an almost photo-realistic way, true colours, living and rich in detail. mediaJET Pearl 300 bright white is a high-quality photo paper for the universal use on all common LFP inkjet plotters using dye-based as well as pigmented inks. The nano-porous coating of this photo paper shows an excellent colour reproduction at high truth of detail, sharpness of outline, an extreme great colour complexity and excellent flatness. mediaJET PEARL 300 bright white is an inkjet paper for highest requirements. The high-resolution mediaJET Pearl 300 bright white has a good fade resistance depending on the ink used.

**Processing**

To guarantee optimal quality, photo and fine art papers should be stored and processed in a climate with 30-70% relative humidity and at temperatures from 15-30°C. We recommend that the paper be acclimatised in the print room for one day before printing, and to reseal in the original package after printing. Prevent fingerprints on the coated side by wearing clean cotton gloves while processing. Please avoid contact with solvent, glue and softener, leads to yellowing.

---

**Technical specification**

---

Material:	Paper	Colour L:	96,6 ± 0,5 %
Application Area:	only indoor	Colour a:	0,9 ± 0,3 %
Surface:	Lustre	Colour b:	-7,85 ± 0,5 %
Specific gravity:	300,00g/m <sup>2</sup>	Specular gloss:	15%
Thickness:	298,00µm	Opacity:	>94%
B1-cert.:	no	Curl, 23°, 50%	0 ± 8 mm
Cold lamination:	yes	Brightness D65°:	108
Heat lamination:	yes	PE-Weight front	15 g ± 2
CIE Whiteness D65°:	150	PE-Weight back	26 g ± 2
		DIN ISO 16245:	no

---

This information consists of standard values for your guidance. Before using our print media, please check their suitability to your printer and for your intended application. Taking account of technical development, product specifications may be amended without prior notice at any time. There is no guarantee that the same results can be achieved. We not accept liability for any errors resulting from technical changes in printers and / or inks.